

Plastic Extruders Ltd


Russell Gardens, Wickford, Essex, SS11 8DN, England
 Sales Tel: +44(0)1268 571116 Fax: +44(0)1268 560027
 www.plastex.co.uk e-mail: sales@plastex.co.uk




Nov-12

PRODUCT DATA SHEET: Herongripa

| Sizes & weights <i>All dimensions are nominal</i> | Tolerances | Length | Height | Widths | | | Weight kg/m ² |
|--|------------|--------|--------|--------|----|-----|-----------------------------|
| | | 0+0.3 | +/-0.5 | +/- 1 | | | |
| | | m | mm | cm | | | |
| Herongripa | | 5 & 10 | 15 | 60 | 91 | 122 | 4.0 |



Herongripa



General

- APPEARANCES** Open grid "duckboard" design with textured surface.
- COLOURS** Available in homogenous standard colour; Terracotta.
- DURABILITY** One piece welded construction for maintenance free life.
- WORKABILITY** Available in rolls for ease of installation. Easy to cut to size and shape.
- USES** For food processing areas.

Technical data

- ACOUSTIC** Excellent sound absorption properties.
- CHEMICAL** Resistant to most acids, alkalines and oils. For specific chemical resistances, see www.plastexmatting.com/matfax/doc.php?doc_id=154&action=inline
- COMPOSITION** Flexible animal fat resistant DINP plasticised Polyvinyl Chloride (PVC) with Steritouch additives.
- ENVIRONMENT** Plastex does not use any substances currently included in the SVHC (Substances of Very High Concern) list under R.E.A.C.H.* in any matting products. All products are 100% recyclable.
 * Registration, Evaluation, Authorisation and Restriction of Chemical substances
- HYGIENE** Non-porous 100% Virgin PVC - Inhibits the growth of bacteria.
 Anti-bacterial SteriTouch additive; Test JIS Z 2801:2000 - Determination of the antibacterial effect against:
 Staphylococcus aureus Result - Antimicrobial pass of >99%
 E. Coli Result - Antimicrobial pass of >99.99%
 Anti-fungal SteriTouch additive; Test method ASTM G21-96 - Determining resistance to fungi.
 Result - Nil Growth after 4 weeks
- REVERSION** Thermoplastic shrinkage can result in size reductions up to 2%. Accelerated in hot environments (refer to www.plastexmatting.com/matfax/doc.php?doc_id=254&action=inline).
- SLIP RESISTANCE** DIN 51130: R11, V10
- THERMAL** Functional -23⁰C +60⁰C (slight size variation may occur at temperature extremes).
- UV LIGHT** Resistant to PVC degradation; uncoloured PVC material - BS EN 607 = Delta E 1.02.
- WARRANTY** 3 years. See www.plastexmatting.com/matfax/doc.php?doc_id=167&action=inline